


## Grupo 654 - "AC" Arruela de Contato Estriada



Ø Nominal	d Tol.		D Tol.		e Tol.		h		Carga de teste kN	h mín. Após 1º teste	Peso Kg/1000
							mín.	máx.			
M 4	4,10	+ 0,3	10,0	± 0,3	1,00	± 0,05	1,15	1,40	4,2	1,05	1,050
M 5	5,10		12,0		1,10		1,45	1,80	6,8	1,30	1,300
M 6	6,10	+ 0,4	14,0		1,20		1,75	2,10	9,0	1,55	1,650
M 8	8,20		18,0		1,50		1,90	2,35	17,5	1,75	1,750
M 10	10,20	+ 0,5	22,0		1,50		2,25	2,75	27	2,05	2,050
M 12	12,40		27,0		1,75		2,60	3,10	40	2,40	2,400
M 16	16,40		32,0	± 0,5	2,50	± 0,06	3,60	4,10	70	3,45	3,450

**Material:** Aço Mola

**Dureza:** 43 a 49 HRc